

OFFICES

SCHOOLS

MUSEUMS

PHARMACIES

RETAIL OUTLETS

LIQUOR STORES

STAFF LOUNGES

ACCESS FLOORING

Commercial Surfacing Specialists

THE **EVOLUTION**
OF RUBBER TILE

Get us under YOUR feet



www.dinoflex.com



DINOFLEX EUROPE

EUROPEAN DISTRIBUTOR OF DINOFLEX RUBBER FLOORING



COMMERCIAL RUBBER
flooring

- Unique Blends
- Vivid Expression
- Dare to be Bold
- Visual Impact
- Dynamic Colors



Irish Moss



Sunflower



Wheat



Baked Clay



custom COLORS



Create a unique blend by mixing and matching from our extensive color palette. The only limit is your imagination.

- | | | | | | | | | |
|---|--|--|--|--|--|---|--|--|
| 
#43 | 
#22 | 
#3C | 
#79 | 
#10 | 
#RB | 
#11 | 
#18 | 
#00 |
| 
#7G | 
#3A | 
#5D | 
#20 | 
#78 | 
#21 | 
#77 | 
#19 | 
#7D |



CUSTOM logos



UNIQUE
CREATIVE
INSPIRED
ORIGINAL
ARTISTIC
APPEALING
FUNCTIONAL

... endless
possibilities!

DESIGNING WITH
THE **EVOLUTION** OF RUBBER TILE



MESQUITE
#004E50



ADOBE
#004E51



MUDDY WATER
#014E52



BAKED CLAY
#001E53



STONE GROUND
#014E54



WHEAT
#004E55




SUNFLOWER
#014E56



OAT MEAL
#014E57



SPANISH MOSS
#514E58



IRISH MOSS
#014E59



PIXIE MOSS
#014E60



GLADE MOSS
#004E61



SAPPHIRE HAZE
#514E62



SMOKY AZURE
#514E63



LIQUID METAL
#014E64



SPUN SILVER
#014E65



BRUSH FIRE
#004E66



MOLTEN LAVA
#014E67



BURNING EMBERS
#014E68



HOT SALSA
#014E69



FOSSIL PAINT
#52P6E18



FOSSIL FUEL
#52P6E20



FERN FOSSIL
#52P6E17



SHELL FOSSIL
#52P6E21

THE **EVOLUTION** OF RUBBER TILE

Physical Properties

TEST	DESCRIPTION	UP TO 50% COLOR	50% - 100% COLOR
ASTM C501	Taber Abrasion (H 22)	0.8% weight loss	4.0% weight loss
ASTM D2047	Static coefficient of Friction (JAMES MACHINE METHOD)	Dry 1.04, Wet 1.05	Dry 0.85, Wet 1.01
ASTM D2240	Hardness Shore A Durometer	64 Indentation	59 Indentation
ASTM D3676	Density Foam Test Summary	66.0 lbs/cu. ft.	78.3 lbs/cu.ft.
ASTM D395B	Compression Set Under Force	96.3% Recovered	94.7% Recovered
ASTM D412	Tensile Strength	290 lbs/sq. in.	186 lbs/sq.in.
ASTM D5116	Materials Emissions VOC	Pass	Pass
ASTM F150 (MFR 98)	Electrical Resistance Surface to Surface Surface to Ground	10 ¹⁶ ohms av 10 ¹⁶ ohms av	10 ¹¹ ohms av 10 ¹¹ ohms av
ASTM F1914-98	Short Term Indentation	.025 in (6.0%) Loss	
ASTM F1914-98	Residual Indentation	.007 in (1.7%) Loss	
ASTM F970-87	Static Load	.000 in (0.0%)	.042 in (10.6%)
ASTM F925-97	Chemical Resistance	no change	no change

Product Specifications

PRODUCT	SIZE	STANDARD THICKNESS
Interlock Tile (Loose Lay)	37" x 37" = 9.5 ft ² 94 cm x 94 cm = 0.88 m ²	5/16", 3/8", 1/2" 8 mm, 10 mm, 12 mm Tolerance of ±0.5mm
Square Cut Tile (Glue Down)	38" x 38" = 10.02 ft ² 96.5 cm x 96.5 cm = 0.93 m ²	5/32", 1/4", 5/16", 3/8", 1/2" 4 mm, 6 mm, 8 mm, 10 mm, 12 mm Tolerance of ±0.5mm

Note: All measurements are subject to nominal variation. For complete specifications and technical data, please see our website at www.dinoflex.com

5 YEAR WARRANTY



DINOFLEX EUROPE

EUROPEAN DISTRIBUTOR OF DINOFLEX RUBBER FLOORING

THE RUBBER SURFACING SPECIALISTS

P.O. Box 3309 TEL (250) 832-7780
5590 - 46th Avenue S.E. FAX (250) 832-7788
Salmon Arm, B.C. TOLL FREE TEL 1-877-713-1899
V1E 4S1 CANADA EMAIL sales@dinoflex.com

www.dinoflex.com

REPRESENTED BY:

Energiestraat 23a
NL-1411 AR Naarden
Tel: +31 (0)35-6782373
Fax: +31 (0)35-6782372
info@dinoflex.nl
www.dinoflex.nl

Get us under YOUR feet.

